

TECHNICAL DATASHEET:

80 Durometer Solid PVC with Plasticizer Block Film 1008

PRODUCT DESCRIPTION

Solid polyvinyl chloride (PVC) mechanically bonded to a polymeric film barrier on one side, which eliminates plasticizer migration when acrylic pressure sensitive adhesive is applied, helping to maintain a long-term bond to many types of substrates.

TYPICAL APPLICATIONS

- Window setting blocks, shims and protective pads.
- Livestock trailers (no skid), dock ramps, and aluminum dock vibration damping
- Aluminum dock decking spacer tape

PRODUCT FEATURES & BENEFITS

- Adhesive has excellent peel and shear values.
- Inexpensive alternative to commercial grade neoprene, rubber and EPDM setting blocks
- Acrylic adhesive gives great high and low temperature and weather resistance
- PVC compound, can be recycled with sash components
- Low/no skid

TECHNICAL DATA	VALUE	TEST METHOD / STANDARD
THICKNESS	1/8"	
FILM THICKNESS	.0005"	
ADHESIVE THICKNESS	.003"	
COLOR	Black	
MATERIAL/SUBSTRATE	Solid Polyvinyl Chloride (PVC)	
DUROMETER/HARDNESS (SHORE A)	75 ±5	ASTM D2240
LINER	78# clay coated	
ADHESIVE SYSTEM	Permanent Adhesive	
ADHESIVE SIDE	Single Sided Adhesive	
ADHESIVE TYPE	Acrylic	
PEEL ADHESION	100 oz./inch	PSTC-1
TENSILE STRENGTH (MINIMUM)	250 lb/in ²	ASTM D412 (DIE C)
SHEAR STRENGTH, (1" x 1" x 1,000G)	100+ hours	PSTC-7
LOOP TACK	109 oz/in	SYNTAC TM
TEAR STRENGTH (MINIMUM)	40 lb/in	ASTM D624 (DIE C)
ELONGATION (MINIMUM)	30%	ASTM D412 (DIE C)
SERVICE TEMPERATURE, SOLID VINYL	-20°F to 200°F	
SERVICE TEMPERATURE, ACRYLIC ADHESIVE	-30°F to 220°F	
ACID RESISTANCE	Yes	

Specifications are believed to be accurate at the time of publication and are subject to change without notice. It is the responsibility of the end-user to test and determine suitability of this material for a particular application. **REV. 0**

TECHNICAL DATASHEET:
80 Durometer Solid PVC with Plasticizer Block Film 1008

TECHNICAL DATA	VALUE	TEST METHOD / STANDARD
ALCOHOL RESISTANCE	Yes	
ALDEHYDES RESISTANCE	Yes	
AMINES RESISTANCE	Yes	
DETERGENT SOLUTIONS RESISTANCE	Yes	
MINERAL OIL RESISTANCE	Yes	
REDUCING AGENTS RESISTANCE	Yes	
RESISTANCE TO ALIPHATIC HYDROCARBON FLUIDS	Yes	

Specifications are believed to be accurate at the time of publication and are subject to change without notice. It is the responsibility of the end-user to test and determine suitability of this material for a particular application. **REV. 0**